

AESSEAL PACKING STYLE 730

100 % PTFE Fiber with Unique Blocking Agent

Characteristics

- · In applications with high pressure or vacuum, die formed bullrings of Style 760 (no food approval) are recommended
- · Very low coefficient of friction and displays low stem/spindle frictions
- · Long lifetime
- · No ageing
- · Minimized maintenance and readjustment

Operating range

| | \$ | ₽ | I |
|---------|-----------|----------|-----|
| p [bar] | 25 | 250 | 500 |
| v [m/s] | 2 | 1.5 | |
| t°C | -200 | . +280 | |
| рН | 0 - 1 | 4 | |
| g/cm³ | 1.60 | | |

Main application

- Valves
- Fittings
- · Gate valves
- Flaps
- Plunger
- · Door and lid seals

Suitable for

- · Pulp and paper industry
- · Chemical industry
- · General Industry





Form of delivery

This packing can be manufactured from 3 to 40 mm square as well as in intermediate, inch sizes and special measurements.

03 - 09 mm on 1 kg spool 10 - 15 mm on 2,5 kg spool

16 - 25 mm on 5 kg spool

Special length, pre-cut or die formed rings on request.

| 1 kg of packing of the following |
|----------------------------------|
| cross-sections is equivalent to |
| displayed meter lengths: |

| Size mm | Meter | Size mm | Meter | |
|------------|-------|------------|-------|----|
| 3 [1/8"] | 57.4 | 13 [1/2"] | 3.9 | |
| 4 | 39.1 | 14 [9/16"] | 3.2 | |
| 5 [3/16"] | 25.0 | 15 | 2.8 | ١. |
| 6 | 17.4 | 16 [5/8"] | 2.4 | |
| 6.4 [1/4"] | 15.5 | 18 | 1.9 | |
| 8 [5/16"] | 9.8 | 19 [3/4"] | 1.7 | |
| 9.5 [3/8"] | 6.9 | 20 | 1.6 | |
| 10 | 6.3 | 22 [7/8"] | 1.3 | |
| 11 [7/16"] | 5.1 | 25 [1"] | 1.0 | |
| 12 | 4.3 | | | |
| | | | | |

All technical information and advice is based on our experience and will be given most conscientiously but without any liability.

Indication and figures are for guidance only and need to be examined by the user. All sizes are subject to manufacturing tolerances. We reserve the right to modify specifications at any time.

Please note that the technical values cannot be used all at the same time in their maximum values.